










Technical Information									
	RLB1000HD	RLR1000	RLB1000NE	RLBKEYLS	RLRKEY	RLBKEYNE	RLBSPLIT	RLBSPLITNE	RLRSPLIT
Available Profile	Plain & Bevel	Plain	Plain & Bevel	Plain & Bevel	Plain	Plain	Plain & Bevel	Plain & Bevel	Plain & Bevel
Length x Width x Height (mm)	1000 x 350 x 350	1000 x 350 x 350	1000 x 350 x 350	1000 x 240 x 350	1000 x 240 x 350	1000 x 240 x 350	1000 x 350 x 165	1000 x 350 x 165	1000 x 350 x 165
No per pallet/pack	8	8	8	11	11	11	12	12	12
Approximate number per m ² (including mortar joint)	2.7	2.7	2.7	2.7	2.7	2.7	5.6	5.6	5.6
Approximate unit weight (kg)	243	260	270	167	170	180	112	132	125
Approximate Weight per m ²	628	675	737	456	460	516	614	754	614
Approximate pallet/pack weight (kg)	1,944	2,080	2,160	1,837	1,870	1,980	1,344	1,584	1,500
Average compressive strength (MPa)	> 5	> 5	> 7	> 5	> 5	> 7	> 5	> 7	> 5
Average block density (kg/m ³)	> 1800	> 1800	> 1900	> 1800	> 1800	> 1900	> 1800	> 1900	> 1800
Co-efficient of contraction (mm/m/15years)	< 0.8	< 0.8	< 0.8	< 0.8	< 0.8	< 0.8	< 0.8	< 0.8	< 0.8
Salt attack resistance category	Exposure	Exposure	Exposure	Exposure	Exposure	Exposure	Exposure	Exposure	Exposure

COLOURS:



LIMESTONE

NATURAL EARTH

All testing is carried out in accordance with Australian/New Zealand Standards AS/NZ4456 or RLMA industry specification test methods where applicable.

Durability classification is based on product knowledge under Perth, Western Australia climatic conditions.

This technical information represents average properties obtained from production lots. If specific test results are required, samples should be taken from current production lots.

Information is subject to change without notice. All colours are indicative only.

Note:

- Sizes and number per square metre or tonne are nominal only and subject to variance due to installation technique, raw and size variations through manufacturing process.
- Retaining wall blocks have one purpose made face.
- Mortar mix recommendation (C:L:S) for M3 application 1:1:6 M4 application 1:0:4.
- Efflorescence is a white powdery deposit that may form on the blocks. It is harmless and appears on the blocks due to external salt sources from surrounding materials such as water, mortar, concrete or salty soils.
- Due to the characteristic nature of the raw materials surface texture variation on the face of the product will vary from block to block and between product runs.
- Ensure any specification or application issues are addressed with Brikmakers prior to order placement.
- RLR Blocks will vary in colour within and between batches.

Please confirm all technical, colour and installation specifications are applicable to your application.